

N35EH

		SI	CGS
Remanence	Br	1.17-1.23 T	11.7-12.3 kG
Coercivity	H _{cb}	≥ 884 kA/m	≥ 11.1 kOe
Intrinsic Coercivity	H _{cj}	≥ 2388 kA/m	≥ 30.0 kOe
Maximum Energy Product	(BH) max	263-287 kJ/m ³	33-36 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	α	-0.11 %/°C	-0.12 %/°C
Temperature Coefficient of H _{cj}	β	-0.47 %/°C	-0.44 %/°C

