

N38EH

		SI	CGS
Remanence	Br	1.22-1.26 T	12.2-12.6 kG
Coercivity	H _{cb}	≥ 923 kA/m	≥ 11.6 kOe
Intrinsic Coercivity	H _{cj}	≥ 2388 kA/m	≥ 30.0 kOe
Maximum Energy Product	(BH) max	287-310 kJ/m ³	36-39 MGOe

		20-140°C	20-180°C
Temperature Coefficient of Br	α	-0.11 %/°C	-0.12 %/°C
Temperature Coefficient of H _{cj}	β	-0.47 %/°C	-0.44 %/°C

