

# N38SH



		SI	CGS
Remanence	Br	1.23-1.30 T	12.3-13.0 kG
Coercivity	Hcb	≥ 923 kA/m	≥ 11.6 kOe
Intrinsic Coercivity	Hcj	≥ 1592 kA/m	≥ 20.0 kOe
Maximum Energy Product	(BH) max	287-318 kJ/m <sup>3</sup>	36-40 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	$\partial$	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	$\beta$	-0.61 %/c	-0.55 %/c

