

N38UH



		SI	CGS
Remanence	Br	1.22-1.28 T	12.2-12.8 kG
Coercivity	H _{cb}	≥ 923 kA/m	≥ 11.6 kOe
Intrinsic Coercivity	H _{cj}	≥ 1990 kA/m	≥ 25.0 kOe
Maximum Energy Product	(BH) _{max}	287-310 kJ/m ³	36-39 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	α	-0.10 %/°C	-0.11 %/°C
Temperature Coefficient of H _{cj}	β	-0.57 %/°C	-0.51 %/°C

