

N40H



		SI	CGS
Remanence	Br	1.26-1.32 T	12.6-13.2 kG
Coercivity	Hcb	≥ 939 kA/m	≥ 11.8 kOe
Intrinsic Coercivity	Hcj	≥ 1353 kA/m	≥ 17.0 kOe
Maximum Energy Product	(BH) max	302-334 kJ/m ³	38-42 MGOe

20-100°C		
Temperature Coefficient of Br	∂	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.65 %/c

