

N44UH

		SI	CGS
Remanence	Br	1.30-1.37 T	13.0-13.7 kG
Coercivity	H _{cb}	≥ 979 kA/m	≥ 12.3 kOe
Intrinsic Coercivity	H _{cj}	≥ 1910 kA/m	≥ 24.0 kOe
Maximum Energy Product	(BH) _{max}	326-358 kJ/m ³	41-45 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	α	-0.10 %/c	-0.11 %/c
Temperature Coefficient of H _{cj}	β	-0.57 %/c	-0.51 %/c

