

N45SH



		SI	CGS
Remanence	Br	1.32-1.38 T	13.2-13.8 kG
Coercivity	Hcb	≥ 987 kA/m	≥ 12.4 kOe
Intrinsic Coercivity	Hcj	≥ 1592 kA/m	≥ 20.0 kOe
Maximum Energy Product	(BH) max	334-366 kJ/m ³	42-46 MGOe

		20-100°C	20-140°C
Temperature Coefficient of Br	∂	-0.11 %/c	-0.12 %/c
Temperature Coefficient of Hcj	β	-0.61 %/c	-0.55 %/c

